

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
22 April 2004 (22.04.2004)

PCT

(10) International Publication Number
WO 2004/033069 A2

(51) International Patent Classification⁷: B01D 39/00

(21) International Application Number:
PCT/FI2003/000748

(22) International Filing Date: 9 October 2003 (09.10.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02/12605 10 October 2002 (10.10.2002) FR

(71) Applicants (for all designated States except US):
AHLSTROM RESEARCH AND SERVICES [FR/FR];
Z.I. de l'Abbaye Impasse Luis Champin, F-38780
Pont-Evêque (FR). AHLSTROM CORPORATION
[FI/FI]; Eteläesplanadi 14, FIN-00130 Helsinki (FI).
AHLSTROM GLASSFIBRE OY [FI/FI]; Ahlströmintie
19, FIN-48600 Karhula (FI).

(72) Inventors; and

(75) Inventors/Applicants (for US only): RÖKMAN, Kay
[FI/FI]; Pyrkönmäenkatu 4 as. 15, FIN-48600 Karhula
(FI). RAHIALA, Hanna [FI/FI]; Karhunkatu 14 E 11,
FIN-48600 Karhula (FI). ESCAFFRE, Pascale [FR/FR];
Chemin des Croix, F-38260 La Cote St Andre (FR).
CHAUVE, Valérie [FR/FR]; 8, Rue des Ursulines,
F-38200 Vienne (FR). DUSSAUD, Joseph [FR/FR]; 40,
Montée Charlemagne, F-38200 Vienne (FR). DUFOUR,
Menno [FR/FR]; 189, rue Vendôme, F-69003 Lyon (FR).
GAUTHIER, Gilles [FR/FR]; 7, rue Richard Wagner,
F-38150 Salaise sur Sanne (FR).

(74) Agent: AHLSTROM KARHULA SERVICES LTD; In-
tellectual Property Department, P.O. Box 18, FIN-48601
Karhula (FI).

(81) Designated States (national): AE, AG, AL, AM, AT (util-
ity model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA,

CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (util-
ity model), DE, DK (utility model), DK, DM, DZ, EC, EE
(utility model), EE, EG, ES, FI (utility model), FI, GB, GD,
GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR,
KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,
MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU,
SC, SD, SE, SG, SK (utility model), SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— as to the identity of the inventor (Rule 4.17(i)) for the fol-
lowing designations AE, AG, AL, AM, AT, AU, AZ, BA, BB,
BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK,
DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI,
NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK,
SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU,
ZA, ZM, ZW. ARIPO patent (GH, GM, KE, LS, MW, MZ,
SD, SL, SZ, TZ, UG, ZM, ZW). Eurasian patent (AM, AZ,
BY, KG, KZ, MD, RU, TJ, TM). European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,
IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR). OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE,
SN, TD, TG)

Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: IMPROVED FILTERING MEDIUM AND USE OF THE SAID FILTERING MEDIUM FOR POLLUTION REMOVAL FROM LAGOONS

(57) Abstract: Filtering medium based on activated carbon which is characterized in that it comprises three superposed layers, respectively an inner layer and two outer layers, the inner layer consisting of 80 to 95% by dry weight of activated carbon, the balance for 100% consisting of organic and/or inorganic chemical fibres, the first outer layer comprising from 45 to 95% by dry weight of organic and/or inorganic chemical fibres, the balance for 100% consisting of activated carbon and/or of a material having a density of less than 0.9, the second outer layer comprising from 5 to 25% by dry weight of activated carbon, the balance for 100% consisting of organic and/or inorganic chemical fibres, and in that the weight of the inner layer is between 40 and 200 g/m² and the weight of the outer layers is between 10 and 100 g/m².

WO 2004/033069 A2

BEST AVAILABLE COPY